

This product was developed and tailored specifically for a new customer application

INTERMEDIATE MODULUS carbon fiber			
PROPERTY	SI UNITS	ENGLISH UNITS	TEST METHOD
Tensile strength	3500 MPa	508 ksi	ASTM D4018
Tensile modulus	275 GPa	40 Msi	ASTM D4018
Strain	1.27%	1.27%	ASTM D4018
Density	1.77 g/cc		
Filament diameter	7 microns		
Sizing type & amount	As specified		
Twist	Never twisted		
Linear density	As specified		
Patents pending			

LET'S WORK TOGETHER TO TAILOR THE EXACT PRODUCTS YOU NEED

CrossLink products are developed and tailored for each customer's specific requirements

For more information:

+1.865.672.6716

[www.CrossLinkComposites.com](http://www.CrossLinkComposites.com)

[info@crosslinkcomposites.com](mailto:info@crosslinkcomposites.com)

The properties listed herein do not constitute any warranty or guarantee of values. This information should only be used for the purposes of material selection. Please contact us for more details. Entire contents copyrighted © 2022 by CrossLink Composites, Inc. All rights reserved.